



# **AW1110**

Fasson<sup>®</sup>
High Gloss
Paper/AP104/P95WH
imp

Fasson®
A mirror finish cast coated paper for high quality printing.

# **Applications**



## **Key Features**

- > This High attractive gloss appearance
- Suitable for a wide range of promotional and industrial label applications

#### **Facestock**

A mirror finish cast coated paper for high quality printing.

Basis Weight: 80 g/m2± 10% ISO536 Caliper: 0.088 mm ± 10% ISO534

#### **Adhesive**

A general purpose permanent, acrylic based adhesive.

#### Liner

A PE coated white kraft paper featuring high strength.

Basis Weight: 96 g/m2  $\pm$  10% ISO536 Caliper: 0.102mm  $\pm$  10% ISO534

#### Performance data

(N/25mm)

loop Tack (st,st)-FTM 9: 16.0 or Tear 20 min 90° Peel (st,st)-FTM 2: 7.5 or Tear 24 hour 90° Peel (st,st)-FTM 2: 9.5 or Tear Minimum Application Temperature: 10°C

After labeling 24Hours, Service Temperature Range: -50°C~+90°C

#### **Adhesive Performance**

The adhesive features excellent initial tack and ultimate bond on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good performance at small cylindrical or overlaminated labels: e.g. cosmetic and pharmaceutical containers.

AP104 is suitable for applications where compliance with FDA 175.105 is required. This section covers applications where for indirect or incidental contact food, cosmetic or drug products.

## **Applications and use**

The product is suitable for a wide range of promotional and industrial label applications where attractive gloss appearance in multicolour work is required.

The above does not represent any guarantee or warranty and the Purchaser must independently determine the suitability of the products for the Purchaser's purposes.

## Conversion/printing

This glossy, coated facestock is specially suited to provide top printing quality in all usual processes, whether single or multicolour, line or process colour printing.


Cares should be taken with the ink viscosity during printing process, too high viscosity of ink will damage the surface of paper.

Excellent conversion characteristics in rotary and flat-bed.

#### Shelf life

One year when stored at 23  $\pm\,2\,^\circ\!\text{C}$  at 50  $\pm\,5\%$  RH.

# Fasson® High Gloss Paper/AP104/P95WH imp



High gloss Paper	
AP104	
P95WH imp	

## Asia Pacific

32/F., Skyline Tower 39 Wang Kwong Road Kowloon Bay, Kowloon, Hong Kong Tel: +852 2802-9618

#### Warrenty

All statements, technical information and recommendations about AVERY DENNISON products are based upon tests believed to be reliable but but do no constitute a guarantee or warranty. All AVERY DENNISON products are sold with the understanding that PURCHASER has independently determined the suitability of such products for its purposes. AVERY DENNISON products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Any product shown to the satisfaction of AVERY DENNISON within the time provided to be so defective shall be replaced without charge of AVERY DENNISON may issue credit in such amount as it seems reasonable however, in no event shall AVERY DENNISON be responsable for claims beyond the replacement value of the defective product or in any way

liable or responsable for consequential or incidental damages. NO EXPRESS WARRANTIES, WHETHER OF MERCHANTIBILITY OR FITNESS FOR ANY ARTICULAR USE, OR OTHERWISE, EXCEPT AS SET FORTH ABOVE (WHICH IS MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES) SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERNATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON. OS salesman, representative, or agent of AVERY DENNISON is authorized to give any guarantee, warranty or make any representation contrary to the above.